

**Ausschuss zur gesundheitlichen
Bewertung von Bauprodukten**

**Committee for Health-related
Evaluation of Building Products**

**AgBB - September 2005
Updated List of LCI values 2005 in Part 3**



Ausschuss zur
gesundheitlichen
Bewertung von
Bauprodukten

Committee for
Health-related
Evaluation of
Building Products

A contribution to the Construction Products Directive:

**Health-related Evaluation Procedure
for Volatile Organic Compounds Emissions (VOC and SVOC)
from Building Products**

1 Introduction

The health and comfort of the occupants of indoor spaces is influenced by the indoor climate in a room (in particular temperature and relative humidity) and by potential indoor air pollutants. Such pollutants may be emitted by a variety of sources. Among these sources building products are of particular importance here since their selection is often not within the occupants' discretion and many of them cover large surface areas in a room.

In Germany the use of building products is subject to the provisions of the building codes of the Federal States (Länder). These provisions require that built structures shall be designed, built, and maintained in such a way that life, health or the natural environment are not endangered (§ 3, standard building code (Musterbauordnung MBO)). Building products used in the construction of buildings or integrated in the building have to satisfy these requirements so that chemical, physical or biological influences do not result in any hazard or unacceptable nuisance (§ 16 MBO).

The importance of building products is also accounted for in the European Union by the European Construction Products Directive (CPD) which came into force in 1989 [Council of the European Communities, 1989]. Although this Directive mainly aims at eliminating barriers to trade, it also contains – at least in a general form – provisions that take health aspects into account. The European Construction Products Directive has been transposed into German national legislation by the Building Products Act in 1992 (Bauproduktengesetz)¹ and by amendments of the building codes of the Federal States (Länder).

¹ Building Products Act (BauPG 1992): Act on marketing and free movement of building products to implement Council Directive 89/106/EEC of 21 December 1988 on the approximation of laws, regulations and administrative provisions of the Member States relating to construction products (Bauproduktengesetz – BauPG). Bundesgesetzblatt (Federal Law Gazette) I, No 39 of 14 August 1992, 1495-1501; amendment 1998: publication of the revision of the Building Products Act of 28 April 1988. Bundesgesetzblatt I, No 25 of 8 May 1998, 812-819.

One of the objectives of the building codes of the Federal States (Länder) and of the European Construction Products Directive is to protect the building users' health. This general objective has been formally documented in the Interpretative Document – Essential Requirement N° 3 (“Hygiene, Health and Environment”; ER 3 for short) prepared by the European Commission, which explicitly mentions that indoor pollutants, e.g. volatile organic compounds (VOC), be avoided and controlled [EC, 1994]. The “Guide for Construction Products Assessment under Health Aspects” produced by German Coordination Committee 03 of the Building and Civil Engineering Standards Committee (Normenausschuss Bauwesen) equally serves this specific purpose. Nevertheless, binding and differentiated evaluation procedures are still not available to translate the health-related requirements of the Construction Products Directive into practice.

There is no doubt that the building users' health has to be protected, but it was still not clear how this protection can be realised in detail. In a number of European countries, including Germany, manufacturers and trade associations have made an attempt to provide the user and consumer with information on the building products' quality via quality labels. However, there is no officially accepted procedure yet for the health-related evaluation of building products.

The European Union has also recognised the insufficient implementation of ER3 and has issued a mandate to CEN for implementation of ER3. The mandate² provides for the development of horizontal assessment methods for dangerous substances in and their emission from, construction products. These methods will then be incorporated in the technical specifications for the standardisation and authorisation of construction products.

National and international bodies, in particular the European Collaborative Action (ECA) "Indoor Air Quality and its Impact on Man", have already dealt with the evaluation of VOC emissions from building products in the 1990s. Within ECA, that is now working under the title “Urban Air, Indoor Environment and Human Exposure”, experts from the EU Member States and from Switzerland and Norway are thoroughly examining the specific knowledge available in Europe over a wide range of indoor issues. The results of their work have been published in reports, which contain sufficiently detailed information to be considered as ‘pre-normative’ documents. One of them is Report No 18 "Evaluation of VOC Emissions from Building Products" in which a flow chart for the evaluation procedure of emissions from floor coverings is given as an example [ECA, 1997a].

The Committee for Health-related Evaluation of Building Products, *AgBB*³ (*Ausschuss für die gesundheitliche Bewertung von Bauprodukten*,) considers as one of its main tasks to establish in Germany the fundamentals for a uniform health-related assessment of building products so that the requirements specified in the building codes of the Federal States (Länder) and the Construction Products Directive are satisfied, and an evaluation procedure will result which is as traceable and objective as possible.

² Mandate M366 “Development of horizontal standardised assessment methods for harmonised approaches relating to dangerous substances under the Construction Products Directive (CPD)”. European Commission, DG Enterprise, Brussels, 16 March 2005.

³ Composed of representatives of the health authorities of the *Länder*, the Federal Environmental Agency (UBA) with the *AgBB* Secretariat, the German Institute for Building Technology (DIBt), the Conference of the *Länder* Ministers and Senators responsible for urban development, construction and housing (ARGEBAU), the Federal Institute for Materials Research and Testing (BAM), the Federal Institute for Risk Assessment (BfR) and Coordination Committee 03 – hygiene, health and environmental protection - of the Building and Civil Engineering Standards Committee of the German Institute for Standardisation (DIN-KOA 03)

In the following, the Committee submits a procedural scheme for health-related evaluation of VOC emissions from building products used for application indoors. Within this scheme, volatile organic compounds include compounds within the retention range of C₆ to C₁₆, which are considered both as individual substances and in calculating a sum parameter following the TVOC concept (TVOC = Total Volatile Organic Compounds), and semivolatile organic compounds (SVOC) within the retention range from C₁₆ up to C₂₂.

The scheme was extensively discussed with representatives of manufacturers and professionals after having been published first [AgBB 2000/2001] and at the end of its introductory phase from 2002 to 2004 [Proceedings of the technical dialogues in 2001 and 2004]. The Committee is confident that by adhering to the test values set in the scheme, the minimum requirements of the building codes for health protection with regard to VOC emissions can be met. Even though, initiatives of manufacturers to produce products with less emissions, are supported. Manufacturers can therefore declare better performance parameters for their products (with regard to VOC emissions).

2 Health-related evaluation of VOC emissions from building products

The effects of indoor air pollution have been dealt with in a large number of publications (cf. e.g. [ECA, 1991b; Maroni et al., 1995]). Volatile organic compounds may have effects ranging from odour perception and irritation of the mucous membranes of the eyes, nose and throat to effects on the nervous system and long-term effects. The latter include allergenic and allergy-promoting properties and, in particular, carcinogenic, mutagenic or reprotoxic potential.

The toxicological evaluation of substances from building products can be based on available information which, in the best, includes knowledge on dose-effect-relationships. Such relationships permit to establish concentration levels below which there would be no concern about adverse effects.

The most comprehensive evaluation system is available for the workplace area for which there are maximum permitted workplace concentrations (*Maximale Arbeitsplatz-Konzentrationen* - MAK values). However, where hazardous substances are handled at workplaces under typical conditions, much higher substance concentrations than under normal indoor conditions are generally encountered. On the other hand, much shorter exposure times occur at workplaces in comparison to indoor situations. Results must therefore be adjusted by suitable factors when applying them to normal indoor living spaces [ECA, 1997a].

The procedure used to establish auxiliary parameters to evaluate building products, the so-called LCI (Lowest Concentration of Interest)⁴ values, is explained in detail in the introduction of the LCI values listed in the Annex (Part 3 of this document).

The aforementioned evaluation criteria are based on the assessment of individual compounds although building occupants are exposed to a multitude of substances. This is accounted for by the total concentration of volatile organic compounds (TVOC) [Seifert, 1999; ISO 16000 /6]. However, it has to be emphasized that a TVOC guideline value – due to the

⁴ In the original German text the acronym NIK is used standing for *Niedrigste Interessierende Konzentration*, which is the translation of LCI.

varying composition of the VOC mixture occurring in indoor air – cannot be based on toxicological conditions. However, experience shows that with increasing TVOC concentration the likelihood of complaints and adverse health effects also increases [ECA, 1997b].

3 Sensory aspects

Since VOC emission is often combined with odour perception, which may result in health impairment, sensory testing is an important element of the evaluation of building products. However, it has not yet been possible to integrate this aspect into the current evaluation of building products. Although many different odour measurement methods exist [Fischer et al., 1998; ECA, 1999], a harmonised and generally accepted procedure for odour assessment of building products is not yet available.

4 Measurement and evaluation of VOC emissions from building products

4.1 Test chamber method for VOC emissions measurement

VOC emissions from building products can be suitably measured in test chambers. Important parameters that have an influence on the result are temperature, air exchange rate, relative humidity and air velocity in the test chamber, and the amount or surface area of the material in the chamber and the method of sample preparation. The influence of these and other parameters became evident in international intercomparison tests [ECA, 1993; ECA, 1995]. Based on the results of these tests and an earlier publication on the test procedure [ECA, 1991a], a European standard for the determination of emissions from building products was published [E DIN EN 13419 1-3, to become DIN EN ISO 16000-9 to -11 in 2006]. Parts 1 and 2 describe the procedure when using a test chamber and a test cell, respectively. Part 3 covers sampling and storing of samples, and preparation of test specimens.

4.2 Exposure scenarios

To relate the results of test chamber measurements to realistic exposure situations a number of boundary conditions must be assumed. It is most important to consider a scenario that reflects exposure under practical conditions.

According to equation (1) the indoor air concentration C , for a surface-emission source depends on the area-specific emission rate E_a [$\mu\text{g}/(\text{m}^2 \text{h})$] of the product, the air exchange rate n [h^{-1}] in the room considered and the ratio of product surface area A [m^2] to the room volume V [m^3]. Parameters n , A and V can be combined into the new parameter q [$\text{m}^3/(\text{h m}^2)$] called the area-specific air exchange rate.

$$C = \frac{E_a \times A}{n \times V} = E_a / q \quad [\mu\text{g}/\text{m}^3] \quad (1)$$

According to DIN 1946-6 (1994), for residential rooms, the outdoor air flow rate per square metre, i.e. the area-specific air exchange rate is between 1 and 1.5 $\text{m}^3/(\text{h m}^2)$ depending on the actual living area. Taking the upper limit of this range, to be on the safe side, and using equation (1) an air exchange rate of approx. 0.5 h^{-1} is obtained for a room 2.7 m high and with a surface area of 3m x 4m. This value corresponds to the average encountered under practical conditions. Choosing these conditions for the chamber test of, e.g., flooring materials, the substance concentration measured in the test chamber corresponds approximately to that to be expected in such a room. However, differences due to potential sorption effects are not taken into account here.

4.3 Evaluation scheme for volatile organic compounds

For health evaluation, a product has to undergo a series of tests as shown in the flow chart in Fig. 1. The procedure starts from a product wrapped in an airtight cover. The start of the experiment (t_0) is defined as the time at which the product to be tested is unwrapped and placed into the test chamber or cell. The product remains in the test chamber or cell over the entire period of the test. For certain product groups it is necessary to define special test

conditions. These specific requirements are defined separately (see Approval guidelines for the health-related evaluation of indoor construction products, Part I and Part II [Deutsches Institut für Bautechnik, 2004]). They may also include the definition of criteria for anticipated termination of the emission measurement. In principle, anticipated termination of the test is permitted at the earliest 7 days after placing the test specimen into the chamber and under the condition that the values determined are less than half the requirements for the 28-day values and no significant increase in the concentration of individual substances is observed in comparison to the measurement on day 3. The fulfilment of these criteria has to be sufficiently demonstrated by the testing body.

In accordance with ISO 16000 /6 the following definitions apply for the emission to be determined in the test chamber:

VOC: all individual substances within the retention range $C_6 - C_{16}$

TVOC: sum of the concentration of all individual substances with concentrations equal to or greater than $5 \mu\text{g}/\text{m}^3$ within the retention range $C_6 - C_{16}$

SVOC: all individual substances within the retention range $> C_{16} - C_{22}$

Σ SVOC: sum of the concentration of all individual substances with concentrations equal to or greater than $5 \mu\text{g}/\text{m}^3$ within the retention range $> C_{16} - C_{22}$

The assignment of the individual substances to the retention ranges $C_6 - C_{16}$ and $C_{16} - C_{22}$ is based on the separation on a non-polar column. Individual substances comprise identified and non-identified compounds.

In the AgBB scheme, the identification of all individual substances is based on a presumed uniform detection limit of $1 \mu\text{g}/\text{m}^3$ in order to cover the emission spectrum as fully as possible in a qualitative way.

All individual substances have to be quantified as required⁵ and need to be considered individually and in the summation if their concentration is equal to or greater than $5 \mu\text{g}/\text{m}^3$. Exceptions apply to particularly critical substances; these have to be included in the calculation of R values if their concentration in substance-specific quantification is equal to or greater than $1 \mu\text{g}/\text{m}^3$ (see 4.3.2).

VOC and SVOC shall be measured using Tenax sampling and subsequent thermodesorption and analysis by GC/MSD according to DIN ISO 16000-6. Aldehydes, in particular low-chained aldehydes listed in Group 7 of the list of LCI values, shall be determined using the DNPH method according to DIN ISO 16000-3 (see Note III in the Annex).

The following explanations are given to the flow chart in Figure 1:

4.3.1 Measurement and testing after 3 days

- TVOC₃

A product satisfies the criteria, if the TVOC value after 3 days (TVOC₃) is $\leq 10 \text{ mg}/\text{m}^3$.

- Carcinogenic substances

Every building product has to meet the general requirement of not emitting any carcinogenic, mutagenic or reprotoxic substances. Emission of carcinogenic substances belonging to

⁵ Identified substances with LCI values as well as carcinogens have to be quantified using their individual calibration factors while identified substances without LCI values and non-identified ("unknown") substances are quantified on the basis of toluene equivalents.

categories 1 and 2 according EU Directive 67/548/EEC is first tested at this stage of the flow chart. Substances with mutagenic or reprotoxic properties and those with potential carcinogenic effects (EU category 3) are checked within the LCI concept (see Part 3) and assigned higher safety factors if necessary. Carcinogens have to be quantified in a substance-specific manner.

The sum of all EU categories 1 and 2 carcinogens [EU Directive 67/548/EEC] detected after 3 days shall not exceed 0.01 mg/m³.

- First sensory testing

For determining the equally important sensory properties it will be necessary to agree upon more precise details before an initial sensory test can be performed at this stage of the flow chart. Until an adequate test method is available, there is only a reference in the flow chart to the necessity of a sensory test.

4.3.2 Measurement and testing after 28 days

- TVOC₂₈

In order to assess the long-term behaviour of the VOC emissions from a building product, the TVOC value is determined again after 28 days. This is done in the same way as described for TVOC₃. When calculating the TVOC₂₈ value, in addition to the instructions given in DIN ISO 16000/6, it is important to be as complete as possible in the identification of compounds to permit the evaluation of individual substances.

A product satisfies the criteria, if the TVOC₂₈ value is ≤ 1.0 mg/m³. Products with a TVOC value higher than that are rejected.

- Semivolatile organic compounds (SVOC)

Products that satisfy the criteria for VOC emissions but instead exhibit increased emission of SVOC should not be given advantages. To prevent this from happening the SVOC concentration in the chamber air shall also be determined⁶.

A product satisfies the criteria if the sum of the SVOC concentrations in the chamber air does not exceed 0.1 mg/m³. This corresponds to an additional content of 10 % of the maximum allowable TVOC₂₈ concentration of 1.0 mg/m³. Higher concentrations result in rejection.

- Carcinogenic substances

The emission of carcinogenic substances of EU categories 1 and 2 [EU Directive 67/548/EEC] is tested again, with an emphasis on the long-term behaviour from the user's point of view. The sum of all carcinogens detected shall not exceed the value of 0.001 mg/m³. Higher concentrations result in rejection.

- Second sensory testing

Until the test procedure has been agreed upon finally, the requirement for a second sensory test after 28 days is indicated. The reason for a second test is that chemical reactions may only occur within the product which may lead to odour or other sensory perception.

⁶ Emission of semivolatile organic compounds with a retention time >C₁₆ (hexadecane) can be quantitatively determined by chamber or cell measurements over 28 days using today's modern analysis apparatus up to a volatility comparable to that of docosane (C₂₂ alkane, boiling point 369 °C). According to current knowledge, the analysis semivolatile organic compounds with an even lower volatility will encounter increasing difficulty if the method of Tenax sampling and thermodesorption is used in chamber tests.

- Evaluation of individual substances

In addition to evaluating the emissions of a product via the TVOC value, the evaluation of individual VOC is also necessary. For this purpose all compounds whose concentration in the chamber air equals or exceeds $1 \mu\text{g}/\text{m}^3$ are first identified, listed with their CAS number, and quantified according to the following:

a) VOC assessable via LCI

For a large number of VOC found in indoor air a list of so-called LCI values (Lowest Concentration of Interest see footnote 4) is contained in the Annex. The details of how these LCI values have been derived are documented in the introduction to the list. Listed substances with a concentration exceeding $5 \mu\text{g}/\text{m}^3$ are evaluated based on LCI. They are quantified in a substance-specific manner.

Particularly critical substances with LCI values $\leq 10 \mu\text{g}/\text{m}^3$ shall be included in the evaluation if their concentration equals or exceeds $1 \mu\text{g}/\text{m}^3$.

For the evaluation of each compound i the ratio R_i is established as defined in equation (2).

$$R_i = C_i / \text{LCI}_i \quad (2)$$

where C_i is the chamber concentration of compound i . For $R_i < 1$, it is assumed that there will be no effects. If several compounds with a concentration $> 5 \mu\text{g}/\text{m}^3$ are detected, additivity of effects is assumed and it is required that R , the sum of all R_i , shall not exceed the value 1.

$$R = \text{sum of all } R_i = \text{sum of all ratios } (C_i / \text{LCI}_i) \leq 1 \quad (3)$$

Products which do not fulfil this condition are rejected.

b) VOC not assessable via LCI

In order to avoid the risk of a positive evaluation of a product which emits larger quantities of nonassessable VOC, a limit is set for those VOC which cannot be identified or do not have an LCI value. This limit equals 10 % of the permitted TVOC value, for the sum of such substances. A product meets the criteria when the sum of such VOC determined at concentrations $\geq 0.005 \text{ mg}/\text{m}^3$ does not exceed $0.1 \text{ mg}/\text{m}^3$. Higher concentrations result in rejection.

4.4 Conclusion

A building product which fulfils the requirements set out in the flow chart (see Figure 1) is suitable for use in enclosed building spaces.

5 References

AgBB (Oct. 2000 / Jan.2001) (Ausschuss zur gesundheitlichen Bewertung von Bauprodukten): Vorgehensweise bei der gesundheitlichen Bewertung der Emissionen von flüchtigen organischen Verbindungen (VOC) aus Bauprodukten (Health-related evaluation procedure for VOC from building products). DIBt-Mitteilungen 1/2001, 3-12

Council of the European Communities (1989): Council Directive 89/106/EEC on the approximation of laws, regulations and administrative provisions of the Member States relating to construction products. Official Journal L 40/12-26

DIBt (2004) (Deutsches Institut für Bautechnik): Approval guidelines for the health-related evaluation of indoor construction products, Part I and Part II, DIBt 2004 - Zulassungsgrundsätze zur gesundheitlichen Bewertung von Bauprodukten in Innenräumen – Stand Juni 2004. DIBt-Mitteilungen 4/2004, 119-141

DIN (1994) (Deutsches Institut für Normung): Raumluftechnik, Teil 6: Lüftung von Wohnungen, Anforderungen, Ausführung, Abnahme (VDI-Lüftungsregeln). (Ventilation and air conditioning – Part 6 Ventilation for residential buildings – Requirement, performance, acceptance (VDI Ventilation code of a practice) DIN 1946-6. Deutsches Institut für Normung, Berlin, Sept. 1994

DIN (2003) (Deutsches Institut für Normung): Bauprodukte - Bestimmung der Emissionen von flüchtigen organischen Verbindungen (VOC). Teil 1: Emissionsprüfkammer-Verfahren – E DIN EN 13419-1; Teil 2: Emissionsprüfzellen-Verfahren – E DIN EN 13419-2; Teil 3: Verfahren zur Probenahme, Lagerung der Proben und Vorbereitung der Prüfstücke. E DIN EN 13419-3. (Building products – Determination of the emission of volatile organic compounds – Part 1: Emission test chamber method. Part 2: Emission test cell method. Part 3: Procedure for sampling, storage of samples and preparation of test specimens; German Version E DIN EN 13419 1-3: *These standards are currently being incorporated into the ISO standards series EN ISO 16000 (prEN ISO 16000-9 to -11).*

ISO 16000-6 (December 2004): (Indoor air - Part 6: Determination of volatile organic compounds in indoor and test chamber air by active sampling on Tenax TA® sorbent, thermal desorption and gas chromatography using MS/FID)

ISO 16000-3 (August 2002): (Indoor air - Part 3: Determination of formaldehyde and other carbonyl compounds; Active sampling method)

EN ISO 16000-9 (planned for June 2006): (Indoor air – Part 9: Determination of the emission of volatile organic compounds – Emission test chamber method)

EN ISO 16000-10 (planned for June 2006): (Indoor air – Part 10: Determination of the emission of volatile organic compounds – Emission test cell method)

EN ISO 16000-11 (planned for June 2006): (Indoor air – Part 11: Procedure for sampling, storage of samples and preparation of test specimens)

EC (European Commission) (1994): Mitteilung der Kommission über die Grundlagendokumente. Amtsblatt EG, C 62/1 vom 28.2.1994. (Communication of the Commission with regard to the interpretative documents of Council Directive, 89/106/EEC (construction products). Official Journal C 62 of 28/2/94)

ECA (1991a) (European Collaborative Action "Indoor Air Quality and its Impact on Man"): Guideline for the Characterisation of Volatile Organic Compounds Emitted from Indoor Materials and Products Using Small Test Chambers. Report No. 8, EUR 1593 EN, European Commission, Joint Research Centre, Environment Institute

ECA (1991b) (European Collaborative Action "Indoor Air Quality and its Impact on Man"): Effects of Indoor Air Pollution on Human Health. Report No. 10, EUR 14086 EN, European Commission, Joint Research Centre, Environment Institute

ECA (1993) (European Collaborative Action "Indoor Air Quality and its Impact on Man"): Determination of VOCs emitted from indoor materials and products - Interlaboratory comparison of small chamber measurements. Report No. 13, EUR 15054 EN, European Commission, Joint Research Centre, Environment Institute

ECA (1995) (European Collaborative Action "Indoor Air Quality and its Impact on Man"): Determination of VOCs emitted from indoor materials and products – Second interlaboratory comparison of small chamber measurements. Report No. 16, EUR 16284 EN, European Commission, Joint Research Centre, Environment Institute

ECA (1997a) (European Collaborative Action "Indoor Air Quality and its Impact on Man"): Evaluation of VOC Emissions from Building Products – Solid Flooring Materials. Report No. 18, EUR 17334 EN, European Commission, Joint Research Centre, Environment Institute

ECA (1997b) (European Collaborative Action "Indoor Air Quality and its Impact on Man"): Total Volatile Organic Compounds (TVOC) in Indoor Air Quality Investigations. Report No. 19, EUR 17675 EN, European Commission, Joint Research Centre, Environment Institute

ECA (1999) (European Collaborative Action "Indoor Air Quality and its Impact on Man"): Sensory Evaluation of Indoor Air Quality. Report No. 20, EUR 18676 EN, European Commission, Joint Research Centre, Environment Institute

EU Directive 67/548/EEC Council Directive 67/548/EEC of 27 June 1967 on the approximation of laws, regulations and administrative provisions relating to the classification, packaging and labelling of dangerous substances, Official Journal 196, 16/08/1967 P. 0001 - 0098


Fischer, J., Englert, N., Seifert, B. (1998): Luftverunreinigungen und geruchliche Wahrnehmungen unter besonderer Berücksichtigung von Innenräumen. (Air pollutants and sensory perception with special regard to the indoor environment) WaBoLu-Hefte 1/1998. Umweltbundesamt, Institut für Wasser-, Boden- und Lufthygiene, Berlin. 110 S. ISSN 0175-4211

Maroni, M., Seifert, B. und Lindvall, T. (1995) Eds: Indoor Air Quality, a Comprehensive Reference Book; Air Quality Monographs – Vol 3; Elsevier Amsterdam 1995

Proceedings: AgBB – UBA – DIBt (2004): 2. Fachgespräch zur Vorgehensweise bei der gesundheitlichen Bewertung der Emissionen von flüchtigen organischen Verbindungen (VOC) aus Bauprodukten (2nd technical dialogue on the procedure for the health assessment of emissions of volatile organic compounds (VOCs) from building products). Held 25 November 2004 at the Federal Institute of Civil Engineering (DIBt). Umweltbundesamt, 2005, <http://www.umweltbundesamt.org/fpdf-1/2898.pdf>. The proceedings from the first technical dialogue are out of print, but were available to the participants of that discussion.

Seifert, B. (1999): Richtwerte für die Innenraumluft: TVOC.(Evaluation of Indoor Air Quality using the sum of volatile organic compounds (TVOC value) Bundesgesundheitsblatt 42 (3), 270-278

Fig. 1: FLOW CHART FOR THE EVALUATION OF VOC* AND SVOC* EMISSIONS FROM BUILDING PRODUCTS



 Generally accepted methods for sensory tests expected to be performed at this stage have yet to be agreed upon.

* VOC, TVOC: Retention range C₆ – C₁₆, SVOC: Retention range C₁₆ – C₂₂

** LCI: Lowest Concentration of Interest (German: NIK)

European Emission Test Standard prEN ISO 16000-9 to -11

UBA II 1.2 - AgBB
Sept. 2005

6. Annex

Establishing LCI values

1. Basic Considerations

Volatile organic compounds (VOC and SVOC) belong to the most common indoor air pollutants. Building products are important indoor sources of VOC and SVOC. In order to be fit for use under the building regulations, building products must satisfy certain health-related provisions with regard to their VOC/SVOC emissions in addition to technical criteria. This means that their emissions (technically speaking: their product- and material-specific emission factors in $\mu\text{g}/\text{m}^2 \text{ h}$) must be reduced to such a level that – assuming long-term occupancy of a room - concentrations in indoor air resulting from such emissions do not pose any threat to the health of sensitive persons even under unfavourable but still realistic assumptions (concerning product loading factor, air exchange rate and indoor climate conditions). A procedure is presented here to derive substance-specific values for health-related evaluation of the emission from building products, the so-called LCI values (Lowest Concentration of Interest; cf. footnote 4).

The concentration of many substances present in workplace air in the form of gas, vapour or suspended particulate matter is limited by workplace regulations (Maximale Arbeitsplatz-Konzentration”, MAK-value; Maximum Workplace Concentration) to ensure that the health of employees is not impaired and that they are not unduly discomforted even by repeated and extended (up to a normal 8-hour day within an average 40-hour working week) exposure, as judged by the current state of knowledge. MAK values are updated continuously and published in an official list [TRGS 900, 2004]. Compliance is checked by measurements. A working group of AgBB – complemented by manufacturers’ specialists - deals with the establishment of LCI values and in doing so uses existing MAK values as a starting point, as proposed by an international expert group [ECA, 1997]. The following basic differences are valid for general indoor spaces (such as homes, kindergartens and schools) as opposed to workplaces:

- continuous exposure in contrast to a changing and regularly interrupted workplace exposure,
- existence of risk groups which are not present in the workplace at all (children, senior citizens) or are particularly protected by occupational medicine (pregnant women, allergic persons),
- lack of exposure measurements and medical checks and, in principle, undefined overall indoor exposure.

On both objective and regulatory grounds, the LCI values for individual compounds are to be considered as calculation values used for the evaluation or certification of building products and not as indoor air limit values. Due to their origin the LCI values represent an adequate expression of the criteria required in building regulations to safeguard against health risk caused by VOC/SVOC mixtures bearing in mind that the emissions from building products into indoor air result in multi-compound mixtures.

2. Procedure

Since the German regulation TRGS 900 (TRGS: Technical Regulations for Hazardous Substances), does not contain values for all VOC/SVOC possibly emitted from building products, a simplified method has been developed that permits to make use, in addition to the

TRGS, of similar (workplace-related) values employed by other European countries. A stepwise procedure is used that takes into account the maximum currently available toxicological evidence for each individual substance, thus enabling the assessment of as many substances as possible. Those substances that still cannot be evaluated, are subjected to a strict limitation of their total amount, within the AgBB scheme. The selection criteria are:

- I. First, each individual substance is checked, whether it has been evaluated via TRGS 900 and/or an OEL (Occupational Exposure Limit) value by the European Commission. If this is the case, the lowest value is used to establish the LCI value.
- II. If condition I is not met, relevant evaluation lists of substances in the workplace air of other EU countries are examined and the lowest value used to establish a LCI value.
- III. If no European legal classification is available, but a MAK value of the German Research Association (Deutsche Forschungsgemeinschaft, DFG) and/or a TLV[®] value of the American Conference of Governmental Industrial Hygienists (ACGIH) or a Workplace Environmental Exposure Limit (WEEL) of AIHA (American Industrial Hygiene Association) exists, then the LCI value is derived from the lowest value available.
- IV. In case a substance cannot be evaluated using conditions I., II. or III., it is checked if an individual substance assessment can be performed, preferably by referring to a substance class with similar chemical structure and comparable toxicological assessment. The lowest LCI value for a substance within this assigned substance class is then used.
- V. If a substance fails to meet any of the requirements in items I. to IV., it is then assigned in the scheme to the category of the substances 'with unknown LCI value', the so-called nonassessable compounds (see flow chart). Non-identified substances fall also into this category.

3. Calculation

Since different exposure times and different sensitivity should be considered in the general population in comparison to workplace conditions, the relevant (MAK) value is generally divided by 100 (except for irritants) applying safety factors as defined elsewhere[ad-hoc-AG, 1996]). For potential carcinogenic substances of EU category 3 (EU Directive 67/548/EEC) the value is usually divided by 1000. Reprotoxic and mutagenic substances are subjected to an individual substance assessment. Substances with carcinogenic properties according to EU categories 1 and 2 (EU Directive 67/548/EEC) are considered separately (see main text for AgBB evaluation scheme).

4. Publication

The LCI values are exclusively determined by the AgBB committee together with experts of industrial and manufacturer associations and published in the list of LCI values. The current list of LCI values and brief notes on their origin are printed in Table 1. AgBB and manufacturers perform individual assessments for currently interesting substances regularly or if there is a need. The LCI list is a closed list which is revised and re-published approximately, depending on the needs, currently every year.

For substances not yet included in the list of LCI values, manufacturers have the possibility to apply for LCI values to be established by submitting available data to the AgBB.

For transparency in establishing LCI values, the published list of LCI values contains, as a minimum, the following data:

- (1) Name(s) of substance

- (2) CAS No.
- (3) LCI value
- (4) The value used for the derivation, with source and substance-related classifications
- (5) Remarks that may provide additional information on the substance or the basis for the LCI setting procedure.

Literature:

ad-hoc-AG (ad-hoc-Arbeitsgruppe aus Mitgliedern der Innenraumlufthygiene-Kommission des Umweltbundesamts und Vertretern der Arbeitsgemeinschaft der Obersten Landesgesundheitsbehörden [AOLG]) (1996): Richtwerte für die Innenraumluft: Basisschema (Guidelines for Indoor Air Quality: Basic Scheme). Bundesgesundheitsblatt 39 (11), 422-426.

ECA (1997) (European Collaborative Action "Indoor Air Quality and its Impact on Man"): Evaluation of VOC Emissions from Building Products – Solid Flooring Materials. Report No. 18, EUR 17334 EN, European Commission, Joint Research Centre, Environment Institute.

TRGS 900: (TRGS: (German) Technical Rules on Hazardous Substances) Technische Regeln für Gefahrstoffe: Grenzwerte in der Luft am Arbeitsplatz, „Luftgrenzwerte“ (Limit values relating to air in the workplace), Bundesarbeitsblatt (BArbBl) Ausgabe Oktober 2000, zuletzt geändert. Heft 5/2004 (Federal Labour Gazette). Bekanntmachung des BMWA vom 31. Dezember 2004 – IIIb3-35122 zur Anwendung der TRGS vor dem Hintergrund der neuen Gefahrstoffverordnung (Promulgation of the Federal Ministry of Economics and Labour of 31 December 2004 – IIIb3-35122 for applying the TRGS in context of the new Ordinance on Hazardous Substances).

Table 1

List of LCI values

Status: September 2005

	Substance	CAS No.	LCI [µg/m ³]	EU OEL [µg/m ³ **]	TRGS 900 [µg/m ³ **]	Remarks**
1. Aromatic hydrocarbons						
1-1*	Toluene	108-88-3	1 900		190 000	EU: Repr. Cat. 3
1-2	Ethyl benzene	100-41-4	4 400		440 000	
1-3	Xylene, mix of o-, m- and p-xylene isomers	1330-20-7	2 200	221 000	440 000	
1-4	p-Xylene	106-42-3	2 200	221 000	440 000	
1-5	m-Xylene	108-38-3	2 200	221 000	440 000	
1-6	o-Xylene	95-47-6	2 200	221 000	440 000	
1-7	Cumene	98-82-8	1 000	100 000	250 000	
1-8	n-Propyl benzene	103-65-1	1 000			cf. lowest LCI of saturated alkylbenzenes, e.g. No1-10
1-9*	1-Propenyl benzene (β-methyl styrene)	637-50-3	2 400			EU-OEL for α-methyl styrene
1-10	1.3.5-Trimethylbenzene	108-67-8	1 000	100 000	100 000	
1-11	1.2.4-Trimethylbenzene	95-63-6	1 000	100 000	100 000	
1-12	1.2.3-Trimethylbenzene	526-73-8	1 000	100 000	100 000	
1-13	2-Ethyltoluene	611-14-3	1 000			cf. lowest LCI of saturated alkylbenzenes
1-14*	1-Isopropyl-2-methylbenzene (o-cymene)	527-84-4	1 100			cf. lowest LCI of saturated alkylbenzenes; conversion via molecular weight
1-15*	1-Isopropyl-3-	535-77-3	1 100			cf. lowest LCI of saturated

	Substance	CAS No.	LCI [µg/m ³]	EU OEL [µg/m ³ **]	TRGS 900 [µg/m ³ **]	Remarks**
	methylbenzene (m-cymene)					alkylbenzenes; conversion via molecular weight
1-16*	1-Isopropyl-4-methylbenzene (p-cymene)	99-87-6	1 100			cf. lowest LCI of saturated alkylbenzenes; conversion via molecular weight
1-17*	1.2.4.5-Tetramethylbenzene	95-93-2	1 100			cf. lowest LCI of saturated alkylbenzenes; conversion via molecular weight
1-18*	n-Butylbenzene	104-51-8	1 100			cf. lowest LCI of saturated alkylbenzenes; conversion via molecular weight
1-19*	1.3-Diisopropylbenzene	99-62-7	1 400			cf. lowest LCI of saturated alkylbenzenes; conversion via molecular weight
1-20*	1.4-Diisopropylbenzene	100-18-5	1 400			cf. lowest LCI of saturated alkylbenzenes; conversion via molecular weight
1-21*	Phenyloctane and isomers	2189-60-8	1,600			cf. lowest LCI of saturated alkylbenzenes; conversion via molecular weight
1-22*	1-Phenyldecane and isomers	104-72-3	1 800			cf. lowest LCI of saturated alkylbenzenes; conversion via molecular weight
1-23*	1-Phenylundecane and isomers	6742-54-7	1 900			cf. lowest LCI of saturated alkylbenzenes; conversion via molecular weight
1-24*	4-Phenyl cyclohexene (4-PCH)	4994-16-5	1 300			cf. styrene; conversion via molecular weight
1-25	Styrene	100-42-5	860		86 000	
1-26*	Phenyl acetylene	536-74-3	840			cf. styrene; conversion via molecular weight
1-27	2-Phenylpropene (α-Methylstyrene)	98-83-9	2 400	246 000	490 000	
1-28	Vinyl toluene (all isomers: o-,m-,p-methyl styrenes)	25013-15-4	4 900		490 000	
1-29	Other alkylbenzenes, unless individual isomers have to be evaluated otherwise		1 000			cf. lowest LCI of saturated alkylbenzenes
1-30	Naphthalene	91-20-3	50	50 000	50 000	EU: Carc.Cat. 3 (29.ATP)
1-31	Indene	95-13-6	450		45 000	
2. Saturated aliphatic hydrocarbons (n-, iso- and cyclo-)						
2-1	3-Methylpentane	96-14-0	7 200		720 000	VVOC
2-2	n-Hexane	110-54-3	72	72 000	180 000	EU: Repr.Cat.3
2-3	Cyclohexane	110-82-7	7 000		700 000	
2-4	Methyl cyclohexane	108-87-2	20 000		2 000 000	
2-5*	1.4-Dimethyl cyclohexane	589-90-2	21 000			cf. methylcyclohexane; conversion via molecular weight
2-6*	4-Isopropyl-1-methylcyclohexane	cis : 6069-98-3 trans: 1678-82-6	29 000			cf. methylcyclohexane; conversion via molecular weight
2-7*	C7-C16 saturated n-aliphatic hydrocarbons		21 000			cf. TRGS 900: 2.100.000 µg/m ³ for n-heptane
3. Terpenes						
3-1*	3-Carene	498-15-7	1 400			cf. α-pinene
3-2*	α-Pinene	80-56-8	1 400			TLV DK-EPA: 140.000 µg/m ³

	Substance	CAS No.	LCI [µg/m ³]	EU OEL [µg/m ³]**	TRGS 900 [µg/m ³]**	Remarks**
3-3*	β-Pinene	127-91-3	1 400			TLV DK-EPA: 140.000 µg/m ³
3-4*	Limonene	138-86-3	1 400			TLV DK-EPA: 140.000 µg/m ³
3-5*	Other terpene hydrocarbons		1 400			TLV DK: 140.000 µg/m ³ for turpentine (This group includes all monoterpenes, sesquiterpenes and their oxygen containing derivatives)
4. Aliphatic alcohols						
4-1	Ethanol	64-17-5	9 600		960 000	VVOC
4-2	1-Propanol	71-23-8	2 400			VVOC; OEL-Norway: 45 000 µg/m ³
4-3	2-Propanol	67-63-0	5 000		500 000	VVOC
4-4	Tert-butanol, 2-methylpropanol-2	75-65-0	620		62 000	
4-5	2-Methyl-1-propanol	78-83-1	3 100		310 000	
4-6	1-Butanol	71-36-3	3 100		310 000	
4-7	1-Pentanol	71-41-0	3 600		360 000	
4-8*	1-Hexanol	111-27-3	4 200			cf. 1-butanol; conversion via molecular weight
4-9	Cyclohexanol	108-93-0	2 100		210 000	
4-10	2-Ethyl-1-hexanol	104-76-7	2 700		270 000	
4-11	1-Octanol	111-87-5	2 700			TLV (ACGIH): 270.000 µg/m ³
4-12	4-Hydroxy-4-methylpentane-2-on (diacetone alcohol)	123-42-2	2 400		240 000	
4-13*	C ₄ - C ₁₀ saturated n-aliphatic alcohols		3 100			cf. 1-butanol
5. Aromatic alcohols						
5-1	Phenol	108-95-2	78	7 800	19 000	EU: Mut. Cat. 3 (29 ATP)
5-2	Butylated hydroxytoluene	128-37-0	100		10 E	
5-3	Benzyl alcohol	100-51-6	440			WEEL (AIHA): 44 000 µg/m ³
6. Glycols, Glycol ethers, Glycol esters						
6-1*	Propylene glycol (1,2-Dihydroxypropane)	57-55-6	320			cf. ethanediol; conversion via molecular weight
6-2	Ethanediol	107-21-1	260	52 000	26 000	
6-3	Ethylene glycol-monobutylether	111-76-2	980	98 000	98 000	
6-4	Diethylene glycol	111-46-6	440		44 000	
6-5	Diethylene glycol-monobutylether	112-34-5	1 000		100 000	
6-6	2-Phenoxyethanol	122-99-6	1 100		110 000	
6-7*	Ethylene carbonate	96-49-1	370			cf. ethanediol; conversion via molecular weight
6-8	1-Methoxy propanol-2	107-98-2	1 900	188 000	370 000	
6-9	2,2,4-Trimethyl-1,3-pentane diol, monoisobutyrate (Texanol®)	25265-77-4				suspended due to lack of data
6-10	Butyl glycolate	7397-62-8	550			cf. glycolic acid, metabolite of ethane-1,2-diol; conversion via molecular weight
6-11*	Diethylene glycol monomethyl ether acetate	124-17-4	800			glycolether group; cf. 2-(2-butoxyethoxy)

	Substance	CAS No.	LCI [µg/m³]	EU OEL [µg/m³]**	TRGS 900 [µg/m³]**	Remarks**
						ethanol; conversion via molecular weight
6-12	Dipropylene glycol monomethyl ether	34590-94-8	3 100		310 000	
6-13	2-Methoxyethanol	109-86-4	15			EU: Repr.Cat. 2; DFG-MAK: 15 000 µg/m³
6-14	2-Ethoxyethanol	110-80-5	19			EU: Repr.Cat. 2; DFG-MAK: 19 000 µg/m³
6-15	2-Propoxyethanol	2807-30-9	860			DFG-MAK: 86 000 µg/m³
6-16	2-Methylethoxyethanol	109-59-1	220			DFG-MAK: 22 000 µg/m³
6-17*	2-Hexoxyethanol	112-25-4	1 200			cf. ethylene glycol-monobutyl ether; conversion via molecular weight
6-18	1,2-Dimethoxyethane	110-71-4	19			EU: Repr.Cat. 2; cf. 2-methoxy-ethanol (metabolite methoxyacetic acid); conversion via molecular weight
6-19	1,2-Diethoxyethane	73506-93-1	25			cf. 2-ethoxyethanol (metabolite ethoxyacetic acid); conversion via molecular weight
6-20	2-Methoxyethyl acetate	110-49-6	25			EU: Repr.Cat. 2; DFG-MAK: 25 000 µg/m³
6-21	2-Ethoxyethyl acetate	111-15-9	27			EU: Repr.Cat. 2; DFG-MAK: 27 000 µg/m³
6-22	2-Butoxyethyl acetate	112-07-2	1300			DFG-MAK: 130 000 µg/m³
6-23*	2-(2-Hexoxyethoxy)-ethanol	112-59-4	1 100			cf. 2-hexoxyethanol and diethylene glycol-monobutyl ether; conversion via molecular weight
6-24	1-Methoxy-2-(2-methoxyethoxy) ethane	111-96-6	28			EU: Repr.Cat. 2; DFG-MAK: 28 000 µg/m³
6-25	2-Methoxy-1-propanol	1589-47-5	19			EU: Repr.Cat. 2; DFG-MAK: 19 000 µg/m³
6-26	2-Methoxy-1-propyl acetate	70657-70-4	28			EU: Repr.Cat. 2; DFG-MAK: 28 000 µg/m³
6-27*	Propylene glycol diacetate	623-84-7	670			cf. propylene glycol; conversion via molecular weight
6-28*	Dipropylene glycol	110-98-5 25265-71-8	550		-	cf. diethylene glycol; conversion via molecular weight
6-29*	Dipropylene glycol-monomethyl ether acetate	88917-22-0	3 900			cf. dipropylene glycol-monomethyl ether; conversion via molecular weight
6-30*	Dipropylene glycol-mono-n-propylether	29911-27-1	1 100			cf. diethylene glycol-monobutyl ether; conversion via molecular weight
6-31*	Dipropylene glycol-mono-n-butylether	29911-28-2 35884-42-5	1 200			cf. diethylene glycol-monobutyl ether; conversion via molecular weight
6-32*	Dipropylene glycol-mono-t-butylether	132739-31-2 (Mixture)	1 200			cf. diethylene glycol-monobutyl ether; conversion via molecular weight
6-33	1,4-Butandiol	110-63-4	2000		200000	
6-34	Tripropylene glycol-monomethyl ether	20324-33-8 25498-49-1	1000			Individ. substance evaluation
6-35	Triethylene glycol-dimethyl ether	112-49-2	35			EU: Repr. Cat. 2; cf. 2-methoxy-ethanol (metabolite methoxyacetic

	Substance	CAS No.	LCI [µg/m ³]	EU OEL [µg/m ³ **]	TRGS 900 [µg/m ³ **]	Remarks**
						acid); conversion via molecular weight
6-36	1.2.-Propylene glycol-dimethyl ether	7778-85-0	25			cf. 1,2-dimethoxy-ethane and 2-methoxy-1-propanol; conversion via molecular weight
7. Aldehydes						
7-1	Butanal	123-72-8	640		64 000	VVOC
7-2	Pentanal	110-62-3	1 700		175 000	
7-3*	Hexanal	66-25-1	890			cf. butanal; conversion via molecular weight
7-4*	Heptanal	111-71-7	1 000			cf. butanal; conversion via molecular weight
7-5*	2-Ethyl-hexanal	123-05-7	1 100			cf. butanal; conversion via molecular weight
7-6*	Octanal	124-13-0	1 100			cf. butanal; conversion via molecular weight
7-7*	Nonanal	124-19-6	1 300			cf. butanal; conversion via molecular weight
7-8*	Decanal	112-31-2	1 400			cf. butanal; conversion via molecular weight
7-9	2-Butenal (crotonaldehyde, cis-trans-mix)	4170-30-3 123-73-9 15798-64-8	1		1 000	EU: Mut.Cat.3
7-10*	2-Pentenal	1576-87-0 764-39-6 31424-04-1	12			cf. 2-butenal, but no EU classification as mutagen; conversion via molecular weight
7-11*	2-Hexenal	16635-54-4 6728-26-3 505-57-7 1335-39-3	14			cf. 2-pentenal; conversion via molecular weight
7-12*	2-Heptenal	2463-63-0 18829-55-5 29381-66-6	16			cf. 2-pentenal; conversion via molecular weight
7-13*	2-Octenal	2363-89-5 25447-69-2 20664-46-4 2548-87-0	18			cf. 2-pentenal; conversion via molecular weight
7-14*	2-Nonenal	2463-53-8 30551-15-6 18829-56-6 60784-31-8	20			cf. 2-pentenal; conversion via molecular weight
7-15*	2-Decenal	3913-71-1 2497-25-8 3913-81-3	22			cf. 2-pentenal; conversion via molecular weight
7-16*	2-Undecenal	2463-77-6 53448-07-0	24			cf. 2-pentenal; conversion via molecular weight
7-17	Furfural	98-01-1	20		20 000	EU: Carc.Cat.3
7-18	Glutardialdehyde	111-30-8	4		420	
7-19	Benzaldehyde	100-52-7	90			WEEL (AIHA): 8 800 µg/m ³
8. Ketones						
8-1	Ethylmethylketone	78-93-3	3 000	300 000	600 000	
8-2	3-Methylbutanone-2	563-80-4	7 000		705 000	
8-3	Methylisobutylketone	108-10-1	830		83 000	
8-4	Cyclopentanone	120-92-3	6 900		690 000	
8-5	Cyclohexanone	108-94-1	400	40 800	80 000	
8-6*	2-Methylcyclopentanone	1120-72-5	8 000			cf. cyclopentanone; conversion via molecular weight

	Substance	CAS No.	LCI [µg/m³]	EU OEL [µg/m³]**	TRGS 900 [µg/m³]**	Remarks**
8-7	2-Methylcyclohexanone	583-60-8	2 300		230 000	
8-8	Acetophenone	98-86-2	490			TLV (ACGIH): 49 000 µg/m³
8-9*	1-Hydroxyacetone (2 Propanone, 1-hydroxy-)	116-09-6	300			oxidation product of propylene glycol, cf. ethanediol; conversion via molecular weight
8-10*	see 9-10					
9. Acids						
9-1	Acetic acid	64-19-7	500		25 000	Individual substance evaluation (plausibility)
9-2	Propionic acid	79-09-4	310	31 000	31 000	
9-3*	Isobutyric acid	79-31-2	370			cf. propionic acid; conversion via molecular weight
9-4*	Butyric acid	107-92-6	370			cf. propionic acid; conversion via molecular weight
9-5*	Pivalic acid	75-98-9	420			cf. propionic acid; conversion via molecular weight
9-6*	n-Valeric acid	109-52-4	420			cf. propionic acid; conversion via molecular weight
9-7*	n-Caproic acid	142-62-1	490			cf. propionic acid; conversion via molecular weight
9-8*	n-Heptanoic acid	111-14-8	550			cf. propionic acid; conversion via molecular weight
9-9*	n-Octanoic acid	124-07-2	600			cf. propionic acid; conversion via molecular weight
9-10*	2-Ethylhexane acid	149-57-5	50			EU: Repr.Cat. 3; TLV (ACGIH): 5 000 µg/m³
10. Ester and Lactones						
10-1	Methyl acetate	79-20-9	6 100		610 000	VVOC
10-2	Ethyl acetate	141-78-6	15 000	734 000	1 500 000	VVOC
10-3	Vinyl acetate	108-05-4	36		36 000	VVOC; EU: Carc.Cat.3
10-4	Isopropyl acetate	108-21-4	4 200		420 000	
10-5	Propyl acetate	109-60-4	4 200		420 000	
10-6	2-Methoxy-1-methylethyl acetate	108-65-6	2 700	275 000	270 000	
10-7*	n-Butyl formiate	592-84-7	2 000			TRGS 900: 120 000 µg/m³ for methylformiate; conversion via molecular weight
10-8	Methyl methacrylate	80-62-6	2 100		210 000	
10-9	Other methacrylates		2 100			cf. methylmethacrylate
10-10	Isobutyl acetate	110-19-0	4 800		480 000	
10-11	1-Butyl acetate	123-86-4	4 800		480 000	
10-12*	2-Ethylhexyl acetate	103-09-3	3 500			cf. 2-ethyl-1-hexanol; ; conversion via molecular weight
10-13	Methyl acrylate	96-33-3	180		18 000	
10-14	Ethyl acrylate	140-88-5	210		21 000	
10-15	n-Butyl acrylate	141-32-2	110	11 000	11 000	
10-16	2-Ethylhexyl acrylate	103-11-7	820		82 000	
10-17	Other acrylates (acrylic acid ester)		110			cf. n-butyl acrylate
10-18	Dimethyl adipate	627-93-0	7 300			cf. methanol (metabolite), conversion via molecular

	Substance	CAS No.	LCI [µg/m³]	EU OEL [µg/m³]**	TRGS 900 [µg/m³]**	Remarks**
						weight
10-19	Dibutyl fumarate	105-75-9	4 800			cf. butanol (metabolite), conversion via molecular weight
10-20	Dimethyl succinate	106-65-0	6 200			cf. methanol (metabolite), conversion via molecular weight
10-21	Dimethyl glutarate	1119-40-0	6 800			cf. methanol (metabolite), conversion via molecular weight
10-22	Hexamethylene diacrylate	13048-33-4	10			WEEL (AIHA): 1 000 µg/m³
10-23*	Maleic acid dibutylester	105-76-0	190			Individ. substance evaluation
10-24	Butyrolactone	96-48-0	2 700			Individ. substance evaluation
11. Chlorinated hydrocarbons						
11-1	Tetrachloroethene	127-18-4	340		345 000	EU: Carc.Cat.3
12. Others						
12-1	1,4-Dioxan	123-91-1	73		73 000	EU: Carc.Cat.3
12-2	Caprolactam	105-60-2	50	10 000	5 000	
12-3	N-methyl-2-pyrrolidon	872-50-4	800		80 000	
12-4	Octamethylcyclotetra- siloxane	556-67-2	1 200			EU: Repr.Cat.3 Individ. substance evaluation
12-5	Hexamethylenetetramine	100-97-00	30			OELs Norway/Sweden: TWA 3 000 µg/m³,
12-6	-2-Butanonoxime	96-29-7	20			EU: Carc.Cat.3 Individ. substance evaluation
12-7	Tributyl phosphate	126-73-8	25		2 500	
12-8	Triethyl phosphate	78-40-0	25			cf. tributyl phosphate
12-9*	5-Chloro-2-methyl-2H- isothiazol-3-one (CIT)	26172-554	1			TRGS 900: 50 µg/m³ for a 3:1 mixture with 2-methyl-4- isothiazolin-3-one

*: new or altered in 2005

** for better comparison, concentration values are given in micrograms per cubic meter

VVOC in the list are marked by grey shading. They are not currently considered in the AgBB evaluation scheme.

Additional remarks:

I) Links to lists of carcinogenic substances of categories 1 and 2 according to Directive 67/548/EEC:

- **BGIA**, Berufsgenossenschaftliches Institut für Arbeitsschutz (BG-Institute for Occupational Safety)
<http://www.hvbg.de/d/bia/fac/kmr>
- **BAuA**, Bundesanstalt für Arbeitsschutz und Arbeitsmedizin (Federal Institute for Occupational Safety and Health)
<http://www.baua.de/>

II. Data treatment

A software tool has been developed for the collection and storage of emissions data and the calculation of the test result. This software is available to all testing laboratories. The DIBt requires its use for transmission of emissions data in the context of applications for product authorisation.

III. Analysis of aldehydes

Determination of the emission of saturated and unsaturated aldehydes of Group 7 of the LCI list by gas chromatography poses problems in the concentration range of

interest. For example, in the case of butanal and glutaric dialdehyde, the ratio of the limit of quantification and the LCI value is very small if the GC/MS method with Tenax thermodesorption (DIN ISO 16000-6) is applied. In addition, sampling on Tenax is only suitable to a limited extent for quantitative determination of butanal, butenal and pentanal. Since butenal in particular, but also unsaturated aldehydes and glutaric dialdehyde have a very low LCI value, an analytical method with a particularly low limit of quantification (LOQ) has to be chosen for these substances. The DNPH method with HPLC analysis (DIN ISO 16000-3) is well suited for this purpose due to a LOQ in the range of $< 1\mu\text{g}/\text{m}^3$ for the aldehydes contained in the LCI list.

Therefore, for quantitative determination of aldehydes, in particular butenal, pentenal, pentanal and glutaric aldehyde, the DNHP method should be used for sampling.

Use of the DNHP method enables the quantitative determination not only of aldehydes belonging to the class of VOC, but also of some VVOC such as butanal, acetone, formaldehyde and acetaldehyde. Although the determination of these compounds is not required in the AgBB evaluation scheme, it will generate additional information for product evaluation.